



### ALU 70 XC

Alu 70 XC films are highly effective at reducing solar heat gain, whilst at the same time 3 mm thick (\*on double glazing 4-16-4) continuing to allow some natural light transmission. This film is providing effective protection against solar glare whilst its one-way mirror aspect guarantees privacy from prying eyes.



Fire-resistance rating M1



Storage from -5°C to +40°C 3 YEARS



REACH RoHS compliant RESPECTED

# WIDTHS AVAILABLE:

152 cm

#### **TECHNICAL DATASHEET**

Data calculated based on film applied to clear glass Vertical installation and on standard glass surface\*\*

· · · · · · · · · · · · · · · · · · ·	
Ultraviolet transmission	1 %
Visible light transmission	43 %
Reflection of external visible light	40 %
Reflection of internal visible light	40 %
Total solar energy rejected	65 %
Total solar energy rejected 2*	69 %
Solar ratio:	
Solar energy reflection	44 %
Solar energy absorption	29 %
Solar energy transmission	27 %
Reduction in Solar Glare	67 %
g-value	0.36
u-value	
Shading coefficient	0.2
Installation type : Exterior	
Roll length	30,5 m
Film composition	PET

Colour from the outsideSILVER

#### **INSTALLATION ADVICE**

Clear single pane	¥
Tinted single pane	¥
Reflective tinted single pane	V
Clear double pane	¥
Tinted double pane	V
Reflective tinted double pane	¥
Gas-filled double pane - Low E	¥
STADIP EXT. clear double pane	V
STADIP INT. clear double pane	∀

✓ Yes 

☐ Caution 


ズ Not recommended

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.

## CONSTRUCTION

Thickness

- 1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
- 2. High optical quality polyester, with anti IR metal partic
- deposit
  3. Bonding adhesive
  4. High optical quality polyester
- 5. PS adhesive, glass polymerization within 15 days
- 6. Protection release liner, disposable after installation



#### MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

75 µ