



SAFE 4 C

Safe 4 C films are perfectly transparent and help secure your windows by ensuring that the glass does not shatter, remaining transparent and retaining its overall integrity in the event of an impact, explosion or fire. Comply with European Standard EN 12600.



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



European Standard EN 12600
2B2



REACH RoHS compliant
RESPECTED

WIDTHS AVAILABLE:

- ↔ **122 cm**
- ↔ **152 cm**
- ↔ **183 cm**

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	5 %
Visible light transmission	85 %
Reflection of external visible light	11 %
Reflection of internal visible light	11 %
Total solar energy rejected	19 %
Total solar energy rejected 2*	19 %
Solar ratio :	
Solar energy reflection	9 %
Solar energy absorption	14 %
Solar energy transmission	77 %
Reduction in Solar Glare	14 %
g-value	0.83
u-value	5.7
Shading coefficient	0.9
Tensile strength (kg/cm ²)	28
Elongation at break	125%
Installation type : Interior	
Roll length	30,5 m
Film composition	PET
Thickness	120 μ

Colour from the outside :
TRANSPARENT

CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester
3. Reinforced PS adhesive to accompany the elasticity of the film in case of impact, glass polymerization within 30 days
4. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	✓

✓ Yes ⚠ Caution ✗ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m².